


AD-A132 741 RIGOROUS BOUNDS FOR THE CALCULATED DIELECTRIC CONSTANTS 1/1  
OF FERROELECTRIC POLYMERS(U) NATIONAL BUREAU OF  
STANDARDS WASHINGTON DC POLYMER SCIENCE AN..

UNCLASSIFIED M G BROADHURST AUG 83 TR-21

F/G 20/12 NL

END  
DATE  
FILMED  
10 83  
DTIC



MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

## REPORT DOCUMENTATION PAGE

READ INSTRUCTIONS  
BEFORE COMPLETING FORM

1. REPORT NUMBER Technical Report No. 21	2. GOVT ACCESSION NO. <b>A132 741</b>	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Rigorous Bounds for the Calculated Dielectric Constants of Ferroelectric Polymers	5. TYPE OF REPORT & PERIOD COVERED Technical Report 21	
7. AUTHOR(s) Martin G. Broadhurst	6. PERFORMING ORG. REPORT NUMBER	
9. PERFORMING ORGANIZATION NAME AND ADDRESS National Bureau of Standards Polymer Science and Standards Division Washington, DC 20234	8. CONTRACT OR GRANT NUMBER(s) N00014-83-F0013	
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Arlington, VA 22217	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS Task No. 15439	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	12. REPORT DATE August 1983	
	13. NUMBER OF PAGES 12	
	15. SECURITY CLASS. (of this report)	
	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) <div style="border: 1px solid black; padding: 5px; display: inline-block;">This document has been approved for public release and sale; its distribution is unlimited.</div> according to attached distribution list		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Submitted to Ferroelectrics		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Dielectric constant, polarization, polymer orientation, polyvinylidene fluoride, rigorous bounds, semicrystalline		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A theory is presented for calculating rigorous upper and lower bounds for the dielectric constant of a semicrystalline polymer in terms of the volume fraction of crystalline phase, the dielectric constant of the liquid phase and the anisotropic dielectric tensor of the crystalline phase. Also required are two orientation functions $\langle \cos^2 \alpha \rangle$ where $\theta$ defines the tilt of crystal lamellae and $\alpha$ the orientation of the electric moment of each crystal with respect to the measuring field. Bounds are presented for polyvinylidene fluoride for a variety of orientations.		

DTIC  
ELECT

SEP 21 1983

A

DTIC FILE COPY

DD FORM 1473

1 JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE  
S/N 0102-014-66011

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

0

Task No. 15439

# Rigorous Bounds for the Calculated Dielectric Constants of Ferroelectric Polymers

Martin G. Broadhurst

in

National Bureau of Standards  
Center for Materials Science  
Polymer Science and Standards Division  
Washington, DC



August 22, 1983

DTIC  
SEP 21 1983

This document has been approved for public release  
and sale; its distribution is unlimited.

Application For  
 Miss Gail  
 Miss T.B.  
 Miss Gail  
 Miss Gail  
 Application/  
 Application Codes  
 Application and/or  
 Application Special  
 A

# RIGOROUS BOUNDS FOR THE CALCULATED DIELECTRIC CONSTANTS OF FERROELECTRIC POLYMERS

MARTIN G. BROADHURST

National Bureau of Standards, Washington, D.C. 20234

**Abstract** A theory is presented for calculating rigorous upper and lower bounds for the dielectric constant of a semi-crystalline polymer in terms of the volume fraction of crystalline phase, the dielectric constant of the liquid phase and the anisotropic dielectric tensor of the crystalline phase. Also required are two orientation functions  $\langle \cos^2 \theta \rangle$  and  $\langle \cos^2 \alpha \rangle$  where  $\theta$  defines the tilt of crystal lamellae and  $\alpha$  the orientation of the electric moment of each crystal with respect to the measuring field. Bounds are presented for polyvinylidene fluoride for a variety of orientations.

## INTRODUCTION

The dielectric constants of polyvinylidene fluoride (PVDF) and related ferroelectric polymers and copolymers are of interest in several ways. PVDF has been used for dielectric films in capacitors since long before its ferroelectric properties were recognized. For capacitors, a high- $\epsilon$  dielectric is desirable for reducing capacitor size and cost. (Throughout this paper we use  $\epsilon$  to mean the dielectric constant of a film measured at audio frequencies normal to the larger film surface). The  $\epsilon$  of PVDF is important also in some piezoelectric and pyroelectric applications such as hydrophones and vidicon elements where decreased  $\epsilon$  means increased voltage sensitivity.

Being able to control  $\epsilon$  is often desirable. It has long been recognized that drawing (stretching) a PVDF film raises its  $\epsilon$  and, partly for this reason, PVDF capacitor films are usually either uniaxially or biaxially drawn. Recently, interesting butterfly-shaped dielectric-hysteresis patterns, such as the one shown in Figure 1, have been observed<sup>1</sup>. Here,  $\epsilon$  is measured at 10 Hz while the electric field is cycled at  $3 \times 10^{-4}$  to  $10^{-2}$  Hz between  $\pm 6$  kV. These data show that poling also significantly affects  $\epsilon$ .




FIGURE 1. Room temperature dielectric hysteresis of 6  $\mu\text{m}$ , mostly  $\beta$  phase PVDF film drawn by rolling to 5 times the original length.<sup>1</sup>

Two early models to explain the increase of  $\epsilon$  of PVDF with drawing have been proposed. The first model<sup>2</sup> emphasizes the role of the liquid phase. The molecules are assumed to orient preferentially in the draw direction, so that rotation of the dipoles about the long molecular axis provides an increased contribution to  $\epsilon$ . A second model<sup>3</sup> considers orientation of stacks of crystal and amorphous lamellae. In this model drawing aligns the lamellae normal to the draw direction and thereby increases the electric field in the phase of highest  $\epsilon$ . Both models account for an increase in  $\epsilon$  with drawing. Most researchers have assumed that the liquid phase has the higher  $\epsilon$ . In this paper I will develop more completely the model of oriented liquid-crystal lamellae. This model has a better chance than does the oriented liquid model, of accounting for the dependence of  $\epsilon$  on poling, since the

remnant polarization most probably resides in the crystalline phase<sup>5-8</sup>. I will also present evidence that the highest dielectric constant comes from one direction in the crystalline phase.

An important detailed treatment of the  $\epsilon$  of the liquid-crystal-lamellae model has been published recently by Boyd<sup>4</sup>. He assumed the basic morphology of semicrystalline polymers is thin lamellar crystals separated by thin layers of liquid polymer. He considered the  $\epsilon$  to be isotropic in both phases. He obtained tight and rigorous upper and lower bounds for  $\epsilon$  in three orthogonal directions in terms of a single orientation function  $\langle \cos^2 \theta \rangle$  where  $\theta$  is the angle of tilt of the normal of the lamellar stacks with respect to a reference direction. Here I will modify the theory to account for anisotropic crystalline lamellae. This extension introduces one additional orientation function  $\langle \cos^2 \alpha \rangle$  where  $\alpha$  is the angle between the direction  $\epsilon$  is measured and the electric moments of the crystals. Six orientation functions must be provided to obtain  $\epsilon$  in three orthogonal directions.

#### THEORY

We assume that PVDF has a morphology typical of semicrystalline polymers as shown in Figure 2.

The crystals are shown in a polar, chain-folded orthorhombic crystal phase with different crystal  $\epsilon$ 's,  $\epsilon_c$ , in the  $x'$ ,  $y'$  and  $z'$  directions. The liquid is assumed isotropic with  $\epsilon = \epsilon_l$ . The  $x'$ ,  $y'$  and  $z'$  axes correspond respectively to the direction of the electric moment, the direction normal to both the moment and molecular chain and the direction normal to the crystal lamellae. This structure is a reasonable approximation to any of the polar phases of PVDF.

We now fix a new coordinate system  $x, y, z$  in a sample as shown in Figure 3.

The upper,  $\epsilon_U$ , and lower bounds  $\epsilon_L$ , for  $\epsilon$  are derived from assuming respectively a uniform electric field  $\underline{E}$  and a uniform




FIGURE 2. Assumed morphology and coordinates of a stack of liquid and crystal lamellae




FIGURE 3. Sample-centered coordinate system and orthogonal transformation angles for an arbitrarily oriented liquid-crystal stack



electric displacement  $\underline{D}$  throughout the sample. These bounds are<sup>4</sup>

$$\epsilon_U = \underline{E}^T (\underline{T} \underline{\epsilon} \underline{T}^{-1}) \underline{E} / E_o^2 \quad (1)$$

$$\epsilon_L = \underline{D}^T (\underline{T} \underline{\epsilon}^{-1} \underline{T}^{-1}) \underline{D} / D_o^2 \quad (2)$$

We are concerned here with the  $\epsilon$  in the  $z$  direction only so we choose

$$\underline{E} = \begin{pmatrix} 0 \\ 0 \\ E \end{pmatrix}, \text{ and } \underline{D} = \begin{pmatrix} 0 \\ 0 \\ D \end{pmatrix}. \quad (3)$$

$\underline{E}^T$  and  $\underline{D}^T$  are the transposed vectors of  $\underline{E}$  and  $\underline{D}$ , and  $E_o$  and  $D_o$  are their magnitudes. The dielectric tensors for the stack are

$$\epsilon_S = \begin{pmatrix} \epsilon_S(x') & 0 & 0 \\ 0 & \epsilon_S(y') & 0 \\ 0 & 0 & \epsilon_S(z') \end{pmatrix} \quad (4)$$

and

$$\epsilon_S^{-1} = \begin{pmatrix} \epsilon_S^{-1}(x') & 0 & 0 \\ 0 & \epsilon_S^{-1}(y') & 0 \\ 0 & 0 & \epsilon_S^{-1}(z') \end{pmatrix} \quad (5)$$

$\underline{T}$  is an orthogonal rotational transformation matrix which transforms a vector in the  $x', y', z'$  coordinate system to one in the  $x, y, z$  coordinate system. I used the transformation matrix given by Goldstein<sup>9</sup>,

$$\underline{T} = \begin{pmatrix} \cos\phi \cos\psi - \cos\theta \sin\phi \sin\psi & -\sin\phi \cos\psi - \cos\theta \sin\phi \cos\psi & \sin\theta \sin\phi \\ \cos\psi \sin\phi + \cos\theta \cos\phi \sin\psi & -\sin\psi \sin\phi + \cos\theta \cos\phi \cos\psi & -\sin\theta \cos\phi \\ \sin\theta \sin\psi & \sin\theta \cos\psi & \cos\theta \end{pmatrix} \quad (6)$$

The results of evaluating Eqs. (1) and (2) are:

$$\epsilon_U = (1-A-B)\epsilon_S(x') + B\epsilon_S(y') + A\epsilon_S(z') \quad (7)$$

$$\epsilon_L = 1 / [(1-A-B)/\epsilon_S(x') + B/\epsilon_S(y') + A/\epsilon_S(z')] \quad (8)$$

where

$$A = \langle \cos^2(z'z) \rangle = \langle \cos^2\theta \rangle \quad (9)$$

$$B = \langle \cos^2(x'z) \rangle = \langle (\sin\theta \cos\psi)^2 \rangle = \langle \cos^2\alpha \rangle \quad (10)$$

$$\epsilon_S(x') = (1-V)\epsilon_1 + V\epsilon_c(x') \quad (11)$$

$$\epsilon_s(y') = (1-V)\epsilon_1 + V\epsilon_c(y') \quad (12)$$

$$\epsilon_s(z') = 1/[(1-V)/\epsilon_1 + V/\epsilon_c(z')] \quad (13)$$

where  $V$  is the volume fraction of crystals.

We now need values for  $\epsilon_1$  and the  $\epsilon_c$ 's. Consider the case of  $\beta$ -phase PVDF where the  $\text{CH}_2\text{-CF}_2$  dipole moment is normal to the molecular chain axis. Librational motions of the dipole about the chain axis contribute to  $\epsilon$  in the  $y'$ /direction. The  $\epsilon$  of such a harmonic liblator is given by,

$$\epsilon = 1 + Nm^2 \langle \psi_T^2 \rangle / 2\epsilon_0 kT \quad (14)$$

where for  $\beta$  phase PVDF  $Nm = 0.2 \text{ Cm}^{-2}$  is the remnant dipole moment per unit volume<sup>10</sup>,  $\langle \psi_T^2 \rangle^{1/2} = 16^\circ$  is the root mean squared librational amplitude<sup>10</sup> at  $T = 300\text{K}$ ,  $m = 117 \times 10^{-30} \text{ Cm}$  (equivalent to 10  $\text{CH}_2\text{-CF}_2$  dipoles)<sup>11</sup> is the dipole moment of an effectively independently librating molecular segment,  $k$  is Boltzmann's constant and  $\epsilon_0$  the permittivity of free space. From Eq. (14) we find  $\epsilon_c(y') = 25$ .  $\epsilon_c(x') = \epsilon_c(z') = 3$  are chosen because they result primarily from atomic and electronic displacement polarization.  $\epsilon_1 = 12$  from an  $\epsilon$ -vs-temperature extrapolation of  $\epsilon$  measured above the melting point<sup>12</sup>. We use a typical crystal-volume-fraction of  $V = 0.5$ .

For sample calculations, we consider films whose state of polarization is specified by  $\langle \cos^2 \psi \rangle$  (see Figure 3). For an unpoled sample  $\langle \cos^2 \psi \rangle = \langle \sin^2 \psi \rangle = 1/2$ . For a sample poled as much as possible in the  $z$  direction,  $\langle \cos^2 \psi \rangle = 0$  and for one poled as much as possible in the  $x$ - $y$  plane,  $\langle \cos^2 \psi \rangle = 1$ . For these three limiting cases,  $\psi$  and  $\theta$  are uncorrelated and we can use  $B \equiv \langle (\sin \theta \cos \psi)^2 \rangle = \langle \sin^2 \theta \rangle \langle \cos^2 \psi \rangle$  or  $B = (1-A) \langle \cos^2 \psi \rangle$ . In general, one cannot assume that  $\theta$  and  $\psi$  are uncorrelated and must avoid this simplification.

## RESULTS

The results of the calculation are summarized in Figure 4. The upper and lower bounds on  $\epsilon$  are shown as a function of  $\langle \cos^2 \theta \rangle$




FIGURE 4. Upper and lower bounds on  $\epsilon$  as a function of orientation for PVDF films in different states of polarization

for the three examples given above.  $\langle \cos^2\theta \rangle = 1/3$  for an un-oriented sample.  $\langle \cos^2\theta \rangle < 1/3$  means the lamellae are preferentially aligned parallel to the  $z$  axis and  $\langle \cos^2\theta \rangle > 1/3$  means the lamellae are preferentially aligned parallel with the  $x$ - $y$  plane of the film.

#### DISCUSSION

The results of our analysis are extremely interesting in the following ways:

M. C. BROADHURST

1. We now have a quantitative evaluation of a model for  $\epsilon$  of a ferroelectric semicrystalline polymer and calculated values of  $\epsilon$  for films of PVDF in various states of crystal orientation and polarization. The calculated values of  $\epsilon$  are in good accord with observed data.
2. We can see the limits of  $\epsilon$  that can be achieved by controlling orientation, polarization and crystallinity. We see what conditions must be met to achieve high, low or intermediate values of  $\epsilon$  and what sacrifice must be made for example in polarization to achieve a particular  $\epsilon$ . We can better relate  $\epsilon$  to processing variables such as draw ratio and applied poling fields.
3. We can use the results to better understand the  $\epsilon$  hysteresis of Figure 1 and hence the polarization process in PVDF. In this case, we see that cycling the poling field causes the electric moments to align strongly in the direction of the field at large fields and slightly in the plane of the film at values of field just below the coercive field.
4. We can use the theory to determine the crystal dielectric tensor and the liquid dielectric constant of semicrystalline polymers from orientation functions and the  $\epsilon$ 's measured for semicrystalline films of the polymer. This knowledge is of considerable value in analyzing dielectric relaxation strengths and shapes to obtain their source (liquid or crystalline) and their orientation.
5. The analysis extends Boyds treatment<sup>4</sup> to anisotropic crystals without significantly increasing the complexity of the calculations.

ACKNOWLEDGMENTS

The author appreciates several fruitful discussions with C. M. Guttman of NBS and the partial support of the work provided by the Office of Naval Research.

M. G. BROADHURST

REFERENCES

1. T. Takahashi, M. Date and E. Fukada, Ferroelectrics, 32, 73 (1981).
2. M. E. Baird, P. Blackburn and B. W. Delf, J. Matls. Sci. 10, 1248 (1975).
3. G. R. Davies, U. of Leeds, private communication.
4. R. H. Boyd, J. Polym. Sci., Polym. Phys. Ed. 21, 505 (1983).
5. M. G. Broadhurst and G. T. Davis in, Topics in Modern Physics-Electrets, G. M. Sessler, Ed. (Springer Verlag, Berlin, 1980), Chapter 5.
6. Y. Wada and R. Hayakawa, Jpn. J. Appl. Phys. 15, 2041 (1976).
7. R.G. Kepler and R. A. Anderson, CRC Crit. Rev. Sol. State Mat. Sci. 9, 399 (1980).
8. A. J. Lovinger, Developments in Crystalline Polymers-1, D. C. Bassett, Ed. (Applied Science Publishers, London, 1982), Chapter 5.
9. H. Goldstein, Classical Mechanics, (Addison-Wesley, Cambridge, MA, 1953), Eq. 4-47.
10. M. G. Broadhurst, T. G. Davis, J. E. McKinney and R. E. Collins, J. Appl. Phys. 49, 4992 (1978).
11. R. B. Olsen, J. C. Hicks, M. G. Broadhurst, and G. T. Davis, Appl. Phys. Lett., In press.
12. S. Yano, K. Tadano, K. Aoki and N. Koizumi, J. Polym. Sci. 12, 1875 (1974).

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 North Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
U.S. Army Research Office Attn: CRD-AA-IP P. O. Box 12211 Research Triangle Park, N.C. 27709	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Mr. Vincent Schaper DTNSRDC Code 2803 Annapolis, Maryland 21402	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. M. Broadhurst Bulk Properties Section National Bureau of Standards U. S. Department of Commerce Washington, D.C. 20234	2	Dr. K. D. Pae Department of Mechanics and Materials Science Rutgers University New Brunswick, New Jersey 08903	1
Naval Surface Weapons Center Attn: Dr. J. M. Augl, Dr. B. Hartman White Oak Silver Spring, Maryland 20910	1	NASA-Lewis Research Center Attn: Dr. T. T. Serofini, MS-49-1 2100 Brookpark Road Cleveland, Ohio 44135	1
Dr. G. Goodman Globe Union Incorporated 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1	Dr. Charles H. Sherman Code TD 121 Naval Underwater Systems Center New London, Connecticut 06320	1
Professor Hatsuo Ishida Department of Macromolecular Science Case-Western Reserve University Cleveland, Ohio 44106	1	Dr. William Risen Department of Chemistry Brown University Providence, Rhode Island 02191	1
Dr. David Soong Department of Chemical Engineering University of California Berkeley, California 94720	1	Mr. Robert W. Jones Advanced Projects Manager Hughes Aircraft Company Mail Station D 132 Culver City, California 90230	1
Dr. Curtis W. Frank Department of Chemical Engineering Stanford University Stanford, California 94035	1	Dr. C. Giori IIT Research Institute 10 West 35 Street Chicago, Illinois 60616	1
Picatinny Arsenal Attn: A. M. Anzalone, Building 3401 SMUPA-FR-M-D Dover, New Jersey 07801	1	Dr. R. S. Roe Department of Materials Science and Metallurgical Engineering University of Cincinnati Cincinnati, Ohio 45221	1
Dr. J. K. Gillham Department of Chemistry Princeton University Princeton, New Jersey 08540	1	Dr. Robert E. Cohen Chemical Engineering Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1
Dr. E. Baer Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1	Dr. T. P. Conlon, Jr., Code 3622 Sandia Laboratories Sandia Corporation Albuquerque, New Mexico 87115	1

TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Martin Kaufman Code 38506 Naval Weapons Center China Lake, California 93555	1	Professor C. S. Paik Sung Department of Materials Sciences and Engineering Room 8-109 Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1
Professor S. Senturia Department of Electrical Engineering Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Professor Brian Newman Department of Mechanics and Materials Science Rutgers, The State University Piscataway, New Jersey 08854	1
Dr. T. J. Reinhart, Jr., Chief Composite and Fibrous Materials Branch Nonmetallic Materials Division Department of the Air Force Air Force Materials Laboratory (AFSC) Wright-Patterson AFB, Ohio 45433	1	Dr. John Lundberg School of Textile Engineering Georgia Institute of Technology Atlanta, Georgia 30332	1
Dr. J. Lando Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1	Dr. D. R. Uhlmann Department of Materials Science Massachusetts Institute of Technology Cambridge, MA 02139	1
Dr. J. White Chemical and Metallurgical Engineering University of Tennessee Knoxville, Tennessee 37916	1		
Dr. J. A. Manson Materials Research Center Lehigh University Bethlehem, Pennsylvania 18015	1		
Dr. R. F. Helmreich Contract RD&E Dow Chemical Co. Midland, Michigan 48640	1		
Dr. R. S. Porter Department of Polymer Science and Engineering University of Massachusetts Amherst, Massachusetts 01002	1		
Professor Garth Wilkes Department of Chemical Engineering Virginia Polytechnic Institute and State University Blacksburg, Virginia 24061	1		



